

# VeriShield® V300

## HIGH-DENSITY MODULAR RADIATION SHIELDING


Groundbreaking system of dry stacked shielding modules which interlock to form a tight, leak-free therapy room of any size or shape. Unique sine-wave shapes eliminate straight line seams and provides superior neutron, photon and particle attenuation at the joints. VeriShield construction requires half the space of mass concrete vaults.

VeriShield radiation shielding components are individual modules combined together to form a composite structure to create the required radiation attenuating environment. The constructed system retains the ability to be deconstructed and reused.

VeriShield products are manufactured in a controlled environment and incorporate high Z aggregates (for photon attenuation) as well as neutron additive materials.

The VeriShield photon, neutron and electron shielding modules feature a design that presents a full 100% inter-locking edge. Lapping or alternating of the seams results in the prevention of straight line paths for radiation streaming. Modules interlock together to form a solid and stable structure.

**V300**



Standard VeriShield V300 modules are 5" x 5" x 10" (127 x 127 x 254mm).

Compressive strength is guaranteed to meet 6,580 psi. This product routinely easily surpasses this minimum and is typically on the order of 7,000 psi and above (depending upon final mix ratios). Grout materials will have a lesser compressive strength as water content is increased for working properties.

# Veritas VeriShield® V300 and VeriShield Grout

VeriShield V300 Shielding Modules and High Density Grout are manufactured and packaged in a controlled environment and incorporate high Z aggregates (for photon attenuation) as well as neutron additive materials.

Designed to be mixed with portland cement, VeriShield Grout will remain volume stable in both wet and dry conditions, and remains stable without cracking or lamination from compressive loading, impact, lateral thrust, high heat or continuous vibration.



<b>SIZE</b>	5" x 5" x 10" – 127 x 127 x 254mm
<b>WEIGHT PER MODULE</b>	43 lbs – 19.7 kg
<b>*DENSITY</b>	300 lbs/cu ft – 5 g/cu. cm (median)
<b>COMPRESSIVE STRENGTH</b>	6,580 psi – 462 kgf/cm2
<b>SOLUBILITY</b>	Insoluble
<b>ABSORPTION</b>	3.3%
<b>REACTIVITY</b>	Non-Reactive
<b>MELTING POINT</b>	^2,800°F – 1,538°C
<b>BOILING POINT</b>	N/A

\*Density variances may vary by ±8% due to standard manufacturing tolerances. VeriShield® modular blocks are engineered to meet or exceed industry standards, ensuring 100% radiation shielding effectiveness.

## COMPOSITION INFORMATION

Major Compounds

Chemical Name	CAS Registry Number
Portland Cement	*65997-15-1
Gypsum (calcium sulfate)	13397-24-5
* May contain crystalline silica	14808-60-7

## PHYSICAL/CHEMICAL CHARACTERISTICS

Boiling Point	N/A
Vapor Pressure (mm Hg)	N/A
Melting Point	N/A
Vapor Density (AIR-1)	N/A
Evaporation Rate	N/A
Solubility in Water	N/A
Appearance & Odor	Grey; no odor

## FIRE AND EXPLOSION HAZARD DATA - None

## REACTIVITY DATA

Stability:	Stable
------------	--------

## RADIATION ATTENUATION

Attenuation is based on interpolated data for some energies. The listed TVL's represent the average tenth value thickness after 5 decades of attenuation. First TVT and equilibrium TVL's may be available for thin barrier sections.

Veritas will provide calculations with appropriate safety factors to ensure attenuation requirements are met.

### V300 Attenuation - Primary Barrier (1TVL=)

6MV:	6.5" – 16.5 cm
10MV:	7.4" – 18.7 cm
15MV:	8.2" – 20.8 cm
18MV:	8.4" – 21.4 cm

### V300 Attenuation - Secondary Barrier (1TVL=)

6MV:	5.3" – 13.4 cm
10MV:	5.8" – 14.7 cm
15MV:	6.3" – 15.9 cm
18MV:	6.3" – 15.9 cm

